

Direct observation of spin configurations and classification of switching processes in mesoscopic ferromagnetic rings

M. Kläui, C. A. F. Vaz, and J. A. C. Bland*

*Cavendish Laboratory, University of Cambridge,
Madingley Road, Cambridge, CB3 0HE, U.K.*

T. L. Monchesky and J. Unguris

National Institute of Standards and Technology, Gaithersburg, MD 20899, U.S.A.

SPELEEM group

Sincrotrone Trieste, 34012 Basovizza, Trieste, Italy

L. J. Heyderman

*Laboratory for Micro- and Nanotechnology,
Paul Scherrer Institut, CH-5232 Villigen PSI, Switzerland*

Z. Cui

Rutherford Appleton Laboratory, Chilton Didcot OX11 0QX, United Kingdom

(Dated: November 20, 2002)

Using non-intrusive imaging techniques we have directly observed the nanoscopic details of the magnetization configurations of epitaxial and polycrystalline mesoscopic ring structures with <15 nm resolution. We have found head to head domain walls with different spin structures depending on ring width. Further, we can classify the geometry dependent switching processes according to the number of transitions (single, double, triple) that a ring undergoes in a hysteresis cycle. In the case of triple switching we find a novel state with a complete vortex core present in the ring.

PACS numbers: 75.60.Ej, 75.60.Ch, 75.70.Ak, 85.70.Kh

Understanding and controlling the magnetic properties of small ferromagnetic elements is a major challenge in the rapidly evolving field of nanoscale science. This is not only

due to the fact that these structures allow for the investigation of fundamental physical properties [1] but they also have important applications such as in magnetic random access memory (MRAM) cells [2]. One key issue is to understand and control the magnetic switching precisely. To achieve this one needs firstly to have well defined and reproducible remanent states and secondly, the switching process itself must be simple and reproducible. A possible geometry that fulfills these criteria is the ring geometry, and in particular narrow ferromagnetic rings, which have recently become the focus of intense interest [3–7]. In all the ring geometries investigated so far, macroscopic measurements and micromagnetic simulations suggest the existence of two magnetic states [3, 4, 6, 7]: the flux-closure vortex state and the ‘onion’ state, accessible reversibly from saturation and characterized by the presence of two opposite head to head walls. However, since it is the microscopic spin configuration of the magnetic states that governs the macroscopic magnetic properties and switching, non-intrusive imaging of the microscopic details of the magnetization including the exact spin structure of the head to head domain walls at the nanometer scale is needed in order to understand and control the switching processes [3, 8, 9]. Furthermore the geometry and the magnetocrystalline anisotropy are predicted to determine the microscopic spin structure of the magnetic states [8, 10], for which direct experimental evidence so far is unavailable.

In this Letter we use non-intrusive imaging techniques based on photoemission electron microscopy (PEEM), and for higher resolution, scanning electron microscopy with polarization analysis (SEMPA) to directly observe the different magnetization configurations present in polycrystalline and epitaxial ring geometries, including details of the different types of head to head domain walls. Furthermore the geometry and material dependence of the switching is comprehensively studied using both magneto-optical Kerr effect (MOKE) and micromagnetic simulations. We find additional novel states and transitions that allow us to classify the observed switching behaviour of all mesoscopic rings into three categories. Two methods were used to fabricate micronscale rings, lift-off of polycrystalline Co and Permalloy (NiFe) films grown on naturally oxidized Si(001) [5] and epitaxial growth of Co on prepatterned Si(001)-H substrates [3]. For the latter method, the epitaxial rings were obtained by depositing a trilayer Cu(100)/fcc Co(100)/Cu(100) capped with 4 nm Au on a Si(100) prepatterned wafer in a UHV MBE system (base pressure 3×10^{-10} mbar) [3]. The lift-off rings were fabricated by means of a PMMA mask that was patterned by e-beam [11].

This was followed by the MBE deposition in UHV and lift-off of polycrystalline Co or Permalloy layers and 4 nm of Au to prevent oxidation.

To image the magnetization configurations we chose PEEM and SEMPA, which are non-intrusive techniques in contrast to imaging techniques such as magnetic force microscopy (as shown in MFM imaging of octagonal structures, MFM can influence and even switch the magnetic configurations [6]). Furthermore, unlike MFM, the non-intrusive techniques used here allow us to image even magnetic states with no stray field such as the vortex state. PEEM was carried out at the synchrotron ELETTRA in Trieste [12]. In X-ray magnetic circular dichroism PEEM (XMCDPEEM) the yield of secondary electrons created by excitation with circularly polarized light depends on the dot product $\mathbf{P} \cdot \mathbf{M}$ of the polarization \mathbf{P} and the magnetization direction \mathbf{M} . The secondary electrons are used for imaging by a SPELEEM (Spectroscopic Photo Emission and Low Energy Electron Microscope) and the yield difference is visible as magnetic contrast in the images [12]. To achieve a higher resolution than that possible with MFM or PEEM, scanning electron microscopy with polarization analysis (SEMPA) was performed at the National Institute of Standards and Technology (NIST) [13]. In this technique, a scanning electron microscope geometry is extended to include spin polarization sensitive detection of the scattered electrons. In this study SEMPA was used to measure the in-plane magnetization direction. To investigate the switching behaviour, MOKE was used to measure hysteresis loops as described in Ref. 3. Simulations were computed by solving the micromagnetic equilibrium equation for each applied field on a square mesh, with a 4 nm cell size. A conjugate gradient solver and the OOMMF package [OOM] were used for the energy minimization and yielded similar results. The intrinsic parameters used for Co are: $M_s = 1424 \times 10^3$ A/m, $A = 33 \times 10^{-12}$ J/m and $K_1 = 6.5 \times 10^4$ J/m³ for epitaxial rings while $K_1 = 0$ in the polycrystalline case. For Permalloy we used: $M_s = 800 \times 10^3$ A/m and $A = 13 \times 10^{-12}$ J/m.

As shown in Ref. 3, we can use an appropriate minor loop field path to obtain rings in the onion state or in the vortex state at remanence. Since we measure an array of rings with a switching field distribution we can switch some of the rings into the onion state while some will remain in the vortex state by following the field path indicated by the red arrows in the hysteresis loop in Fig. 1 (a), where the field is relaxed to zero from the middle of the switching field distribution of the vortex to the onion transition [3]. A low resolution

PEEM image of four rings (outer diameter $D=1100$ nm, inner diameter $d=850$ nm and thickness $t=15$ nm polycrystalline Co), taken after relaxation of the field to remanence, is shown in Fig. 1 (b). As expected some rings are still in the vortex state (two rings have a counter-clockwise and one ring has a clockwise circulation direction) while one ring has already switched into the onion state. While it is easy thus to confirm the vortex and onion states with PEEM, the maximum resolution achieved (30 nm) is not sufficient to resolve the details of the exact magnetization configuration such as the structure of the head to head domain walls in the onion state.

To obtain more detailed, higher resolution images we use SEMPA. Higher resolution is essential since micromagnetic simulations predict different types of head to head domain walls [8], and since it is the type of domain wall that characterizes the onion state and is very important to for the switching behaviour investigated in Ref. 9 and for the nucleation- free onion to vortex transition [3]. For epitaxial samples (e.g. fcc cobalt), micromagnetic simulations predict that, in addition to the head to head domain walls that are also present in the onion state of polycrystalline rings, epitaxial samples should show additional domain-like features due to the cubic anisotropy. Furthermore, epitaxial samples of different geometries also allow the study of the interplay between the magnetocrystalline anisotropy and the local shape anisotropy that is due to the dipolar interactions in te the particular geometry. A SEMPA image for a wide epitaxial ring ($D=1600$ nm, $d=900$ nm, $t=34$ nm fcc Co) is shown in Fig. 2 (a). In this wide ring the head to head wall is a vortex wall, since this minimizes the stray field at little cost from the exchange energy term as theoretically predicted [8]. The micromagnetic simulation in Fig. 2 (b) shows remarkable agreement, although the exact position of the head to head domain wall in the experiment is determined by local defects (the highly energetic vortex core is pinned at non-magnetic defects). In addition to the head to head walls, a domain structure is visible in the the SEMPA image and in the simulation demonstrating the influence of the magnetocrystalline anisotropy for this wide ring geometry.

In narrow rings any deviation of the magnetization from parallel to the ring edge will create dipole stray fields. Therefore the magnetization closely follows the shape (local shape anisotropy) and aligns with the circumference. In this case no domain features are expected since the strong local shape anisotropy supersedes the magnetocrystalline

anisotropy. This can be seen in the SEMPA image in Fig. 2 (c) and in the micromagnetic simulation in Fig. 2 (d) of a narrow ring ($D = 1600$ nm, $d=1200$ nm, $t=34$ nm fcc Co). Furthermore in this narrow ring a transverse head to head domain wall is present since a vortex wall would have to be compressed into the narrow ring resulting in a prohibitively high exchange energy. The energetics of the different domain wall types is analysed further in Ref. 8 and the different kinds of domain walls observed here are in good agreement with [8].

While the geometry dependence of the remanent magnetic states can be studied with SEMPA, it is difficult to image while applying magnetic fields. To study the magnetic states and transitions, which develop when a field is applied, we make MOKE measurements on arrays of rings. In the limited range of geometries and materials that have been studied previously [3, 4, 6] only the double switching process discussed above was reported. Here we have varied the film thickness and ring width over a very wide range (film thickness fcc Co 5 nm-34 nm, polycrystalline Co 2 nm-34 nm and polycrystalline Permalloy 2 nm-45 nm, ring width 5%-90% of the outer diameter D , 300 nm $< D < 2000$ nm). D is kept < 2 μ m for mesoscopic rings to prevent the occurrence of complicated and defect dominated multi-domain states.

In addition to the previously found double switching process (Fig. 1 (a), [3, 4]), depending on the geometry we find novel types of hysteresis behaviour: the reversal can occur with a single transition as seen in Fig. 3 (a) or with triple switching as seen in Fig. 3 (b).

To elucidate these different behaviours we consider the transitions that are available for each magnetic state. After relaxing the field from saturation a ring develops the onion state with a wall structure determined by the geometry (see Fig. 2 (a-d)). Additional simulations show that then there are two competing switching processes when a reverse field is applied: (i) for rings made of a thick magnetic film, domain wall depinning followed by propagation leads to the double switching process as seen in Fig. 1 (a) and explained in references 3 and 14; (ii) in rings with a thin film a reverse domain can be nucleated somewhere at the edge of the ring (not necessarily related to the position of the domain walls), which then grows and spreads over the whole ring until the opposite onion state is attained. This process is a nucleation-propagation process similar to that described in detail in [14] but in this case it leads to a single onion to (reverse-) onion switching characterized by a single jump in the M-H loop (Fig. 3 (a)). This process is very unfavourable in thick film rings since the spins are

strongly aligned with the edges. Any deviation from the perimeter would be energetically disadvantageous in this case due to the large dipolar stray field created, whereas in thin rings the necessary twisting of spins to nucleate a reverse domain can happen easily. Furthermore in very thin rings the onion state can be energetically favoured over the vortex state because of the lower exchange energy, which outweighs the small stray field energy of the onion state, so that as seen in Fig. 3 (a) a very thin ring ($t=4$ nm here) switches directly from the onion to the reverse onion state.

To explain the triple switching observed for wide and very thick rings (e.g. the ring geometry for Fig. 3 (b)), we have computed a hysteresis loop for such a ring. As seen in Fig. 3 (b) the simulation reproduces the experimental loop well and the magnetization configurations found are shown schematically. Apart from the onion and vortex state, we observe a new state (schematic in Fig. 3 (b) and micromagnetic simulation of the detailed magnetization configuration in Fig. 3 (c)), which we term the ‘vortexcore’ state (since a complete vortex core is present). This state is not stable at remanence, where the ring reverts to the vortex state. This is because both states have zero stray field but the exchange energy is higher in the vortexcore state due to the presence of the vortex core. In an applied field on the other hand the gain in Zeeman energy in the vortexcore state makes it energetically favourable. As the vortexcore state has to be stabilized by an applied field, it could not be directly imaged with the techniques available, but we can compare the simulated and measured hysteresis loops shown in Fig. 3 (b). The height of the jumps is well reproduced in the simulation. In addition a very sensitive measure for the type of magnetization configuration is the curvature of the loop when the field is applied. As predicted earlier [15] the curvature $d^2 M/dH^2$ of the hysteresis loop is positive when a field is applied to a ring in the vortex state and negative if the ring is in a state where a vortex core is present, such as the vortexcore state. As seen in Fig. 3 (b) and the enlargement of the interesting field region Fig. 3 (d), the curvature after the first switching is positive, which means that the rings have switched from the onion state into the vortex state. After the second jump the curvature is negative, which means that the ring has switched from the vortex to the vortexcore state. This positive curvature is the same as that reported for the case of discs in the vortex state in an applied field [15, 16]. The similarities in the curvature are due to the fact that physically the same process is occurring as the applied field is increased: the component of the magnetization parallel to the field direction grows and hence the vortex core is pushed outwards (in the case of Fig.

3 (b) towards the left) until at the critical field it leaves the structure and the ring attains the onion state. It is now clear why the vortexcore state is only observed in wide and very thick rings: due to the exchange energy it is only possible to ‘fit’ a vortex core into rings above a certain width and only for large thicknesses the energy gain due to the absence of a stray field offsets the higher exchange energy of the vortexcore state.

In conclusion, we have presented the nanoscopic details of the magnetization configurations in mesoscopic rings, which show the influence of geometry and magnetocrystalline anisotropy particularly on the spin structure of the different types of head to head domain walls. The influence of the geometry on the switching processes is evident and three categories of switching behaviour are found. In addition to the double switching process, thin rings show a single reversal mechanism, while very wide rings with a thick film exhibit triple switching and for these rings the novel vortexcore state is shown to occur.

The authors acknowledge support from the Gottlieb Daimler- and Karl Benz Foundation (M.K.), the Office of Naval Research (T.L.M. and J.U.) and the European ESPRIT network MASSDOTS.

Caption:

Fig. 1:

(a): Hysteresis loop measured on an array of rings (outer diameter $D=1200$ nm, inner diameter $d=900$ nm and thickness $t=15$ nm polycrystalline Co). The magnetization configurations of the onion and the vortex states are shown schematically. Red arrows indicate the field path used to obtain the rings in the states imaged with PEEM in (b).

(b): PEEM image of four polycrystalline Co rings. The top ring is in the clockwise vortex state, the bottom and right rings are in the counter-clockwise vortex state and the left ring is in the onion state pointing along the direction of the applied field H . The field of view is $\approx 10 \mu\text{m}$ across and the blue arrow points in the direction of the photon beam. The colour scale indicates the direction of the magnetization with reference to the direction of the incoming photon beam (magnetization parallel to the incoming photon beam (red) to anti-parallel (purple)).

Fig. 2:

Micromagnetic calculations and SEMPA images of the onion state in a wide ($D=1700$ nm, $d=900$ nm) and a narrow ($D=1700$ nm, $d=1200$ nm) epitaxial 34 nm fcc Co ring.

(a) SEMPA image of the wide ring. The vortex walls and the magnetocrystalline anisotropy induced domain structure (marked with S) is visible.

(b) Micromagnetic simulation of the wide ring. In addition to the vortex head to head domain wall, the domain structure is visible (marked with S). The position of the vortex core is slightly different from the SEMPA graph as in the experiment the position is determined by non-magnetic defects that pin the vortex core, which are absent in the simulation. The colour code indicating the direction of the magnetization is shown.

(c) SEMPA image of the narrow ring (only half the ring is shown). No domain structure is seen as the local shape anisotropy dominates over the magnetocrystalline anisotropy. A transverse head to head domain wall is present.

(d) Micromagnetic simulation of the narrow ring exhibiting the transverse domain wall.

Fig. 3:

MOKE loops of an array of rings. (a) Hysteresis loop showing single switching in thin film rings ($D=1700$ nm, $d=1250$ nm, $t=4$ nm polycrystalline Co) with the magnetization config-

urations of the onion states shown schematically.

(b) Triple switching in very wide rings with thick films ($D=1700$ nm, $d=300$ nm, $t=32$ nm polycrystalline Co; experimental data: black line, micromagnetic simulation: empty circles).

The magnetization configurations are shown schematically (from top to bottom: onion, vortex, vortexcore and opposite onion state).

(c) Micromagnetic simulation of the magnetization configuration in the vortexcore state (colour code as in Fig. 2).

(d) Enlargement of the experimental data in the interesting field region showing the difference in curvature when the field is applied to the ring in the vortex state (indicated with pos.) and in the vortexcore state (indicated with neg.)

* Corresponding author; Electronic address: jacb1@phy.cam.ac.uk

- [1] L. D. Landau and E. M. Lifshitz, *Physik Z. Sowjetunion* **8**, 153 (1935).
- [2] J.-G. Zhu, Y. Zheng, and G. A. Prinz, *J. Appl. Phys.* **87**, 6668 (2000).
- [3] J. Rothman, M. Kläui, L. Lopez-Diaz, C. A. F. Vaz, A. Bleloch, J. A. C. Bland, Z. Cui, and R. Speaks, *Phys. Rev. Lett.* **86**, 1098 (2001).
- [4] M. Kläui, J. Rothman, L. Lopez-Diaz, C. A. F. Vaz, J. A. C. Bland, and Z. Cui, *Appl. Phys. Lett.* **78**, 3268 (2001).
- [5] M. Kläui, C. A. F. Vaz, J. A. C. Bland, W. Wernsdorfer, G. Faini, and E. Cambril, *App. Phys. Lett.* **81**, 108 (2002).
- [6] S. P. Li, D. Peyrade, M. Natali, A. Lebib, Y. Chen, U. Ebels, L. D. Buda, and K. Ounadjela, *Phys. Rev. Lett.* **86**, 1102 (2001).
- [7] S. Kasai, T. Niiyama, E. Saitoh, and H. Miyajima, *J. Magn. Magn. Mater.* **239**, 228 (2002).
- [8] R. McMichael and M. Donahue, *IEEE Trans. Magn.* **33**, 4167 (1997).
- [9] L. Lopez-Diaz, M. Kläui, J. Rothman, and J. A. C. Bland, *Physica B* **306**, 211 (2001).
- [10] L. Lopez-Diaz, J. Rothman, M. Kläui, and J. A. C. Bland, *J. Appl. Phys.* **89**, 7579 (2001).
- [11] C. David and D. Hambach, *Microelectron. Eng.* **46**, 219 (1999).
- [12] A. Locatelli, K. S. Cherifi, S. Heun, M. Marsi, K. Ono, A. Pavlovska, and E. Bauer, *Surf. Rev. Lett.* **9**, 171 (2002).
- [13] M. R. Scheinfein, J. Unguris, M. H. Kelley, D. T. Pierce, and R. J. Celotta, *Rev. Sci. Instrum.*

61, 2501 (1990).

[OOM] The free OOMMF package is available at <http://math.nist.gov/oommf>.

[14] M. Kläui, L. Lopez-Diaz, J. Rothman, C. A. F. Vaz, J. A. C. Bland, and Z. Cui, *J. Magn. Magn. Mat.* **240**, 7 (2002).

[15] L. Lopez-Diaz, J. Rothman, M. Kläui, and J. A. C. Bland, *IEEE Trans. Magn.* **36**, 3155 (2000).

[16] R. P. Cowburn, D. K. Koltsov, A. O. Adeyeye, M. E. Welland, and D. M. Tricker, *Phys. Rev. Lett.* **83**, 1042 (1999).