

Aspect-ratio driven evolution of high-order resonant modes and near-field distributions in localized surface phonon polariton nanostructures

Chase T. Ellis¹, Joseph G. Tischler¹, Orest J. Glembocki¹, Francisco J. Bezares^{1,2}, Alexander J. Giles¹, Richard Kasica³, Loretta Shirey¹, Jeffrey C. Owrutsky¹, Dmitry N. Chigrin⁴ and Joshua D. Caldwell.¹

1. U.S. Naval Research Laboratory, Washington, DC, USA.
2. American Society for Engineering Education, Washington, DC, USA.
3. Center for Nanoscale Science and Technology, National Institutes of Standards and Technology, Gaithersburg, MD, USA.
4. I. Institute of Physics (IA), RWTH Aachen University, Aachen, Germany.

Abstract

Polar dielectrics have garnered much attention as an alternative to plasmonic metals in the mid- to long-wave infrared spectral regime due to their low optical losses. Nanoscale resonators composed of these materials have been used to demonstrate figures of merit beyond those achievable in plasmonic equivalents. Until now, only low-order, phonon-mediated, localized polariton resonances, known as surface phonon polaritons, have been observed in polar dielectric materials. In the present work we investigate the excitation of 17 distinct high-order, multipolar localized surface phonon polariton resonances that are optically excited in rectangular pillars etched into a semi-insulating silicon carbide substrate. The presence of these high-order multipolar modes is due to the sharp corners of the nanostructures that are not present in structures with higher degrees of symmetry (e.g., spheres, ellipsoids, cylinders, etc...). By elongating a single axis of the pillars we are able to significantly modify the far- and near-field properties of localized surface phonon polariton resonances, opening the door to realizing tailored narrow-band infrared sources. Such control of the near-field behavior of resonances can impact surface enhanced optical sensing, which is mediated by polarization selection rules that depend on the local near-fields of nearby resonators, as well as the morphology and strength of resonator hot spots. Furthermore, through the careful choice of polar dielectric material, these results can also serve as the guiding principles for the generalized design of optical devices that operate from the mid- to far-infrared.

Manuscript

[Introduction](#)

The quasiparticle excitation that arises from interactions between coherent charge oscillations and electromagnetic radiation, known as an optical polariton, gives rise to a wide variety of near-field optical phenomena that enable the control and manipulation of light in the sub-diffractive regime.^{1,2} This regime is not ordinarily accessible via free-space optics, which is limited by the Abbe diffraction limit. However, under the right conditions, light impinging upon a nanostructure much smaller than the wavelength of light can excite optical polariton resonances that strongly confine fields near the surface, resulting in the enhancement of local electromagnetic fields and emission/absorption rates of nearby

devices. In such situations these resonances are able to greatly alter the near-field radiation pattern at the nanoscale, which has had a profound influence on nanophotonic technologies, such as waveguides,³⁻⁵ light sources,⁶ near-field optics,⁷⁻⁹ solar cells,^{10,11} chemical sensors,¹² biosensors,^{13,14} photonic circuitry,¹⁵⁻¹⁷ and even cancer therapy.¹⁸ Thus far, the majority of these technologies exploit electron plasmas in metals in order to excite and harness the power of optical polaritons (surface plasmon polaritons, SPPs) in the ultraviolet to near-infrared spectral regimes. Due to the high dispersion in the real part of the dielectric function and the corresponding steady increase in optical losses in the mid- to far-infrared regimes, the performance of metals for infrared nanophotonic applications is limited.¹⁹ An alternative system that is not subject to these limitations employs polar dielectric crystals that are capable of supporting phonon-mediated, collective oscillations of bound lattice charges that sustain a plasmonic-like, sub-diffractive excitation over the infrared spectral range bounded by the longitudinal (LO) and transverse (TO) optic phonon frequencies (ω_{LO} and ω_{TO}), known as the Reststrahlen band.²⁰⁻²³ Such excitations, known as surface phonon polaritons (SPhPs), usually occur in the mid- to long-wave infrared spectral regime and are subject to significantly lower losses, in comparison to metals, in the infrared due to the long lifetimes of optic phonons ($\tau \approx 1-100$ ps) from which they are derived. These lifetimes are over an order of magnitude longer than the scattering times of free carriers in metals.²⁴ Moreover, low optical losses are of distinct importance for potential applications, as evidenced by the higher figures of merit reported, such as the quality factor^{21,25,26} and Purcell factor,²¹ for SPhP materials. As such, these qualities provide an opportunity for SPhP materials to greatly influence nanophotonic technologies in the infrared spectral regime.^{27,28} However, the realization of such opportunities hinges on the ability to understand, control, and manipulate near-field radiation patterns via the excitation of plasmonic-like resonances that are excited in polar dielectric materials, which is the main concern of this letter.

For isolated nanoparticles with dimensions much smaller than the wavelength of light ($d \ll \lambda$), the incident electric field is nearly homogeneous over the space occupied by the particle (quasi-static regime). In this regime, considering the case of a non-interacting nanosphere, the dominant localized optical polariton resonance consists of a simple dipole that is aligned parallel to the incoming light polarization. However, altering the nanoparticle environment, shape, and size can significantly modify this resonance, leading to new resonances that deviate from such simplified conditions. For example, by increasing the nanostructure size, retardation effects within the optical resonator become important, that is, the phase of the incident electric field varies over the nanostructure dimensions, resulting in the excitation of higher order multipoles.²⁹⁻³¹ In addition, symmetry breaking, which is introduced by interactions between adjacent nanostructures³² or a nanostructure and a nearby substrate,^{33,34} can result in the hybridization of allowed dipole and unallowed higher-order resonant modes. Furthermore, changing the shape and therefore the symmetry of plasmonic nanoparticles has a profound effect on the various localized optical polariton resonances that can be optically excited. This effect is clearly seen by comparing the extinction spectra for isolated spherical and cubic nanoparticles of subwavelength dimensions, where the quasi-static regime ($d \ll \lambda$) is applicable and retardation effects are negligible.^{35,36} While the nanosphere spectra consists of only a single dipole resonance, the isolated nanocube spectra reveals many resonances that include this dipole resonance, as well as many other higher-order modes with more complicated near-field radiation patterns.³⁶⁻³⁹ The simplicity of the spherical optical resonance stems from the fact that this geometry is only capable of supporting a homogeneous polarization in the quasi-static regime. However, for the case of the cube, corners and

edges are able to concentrate charge, leading to many non-homogeneous polarization configurations. By changing and controlling the configuration of charge concentration, one also controls the areas where near-field enhancement occurs. To date, optical studies of localized SPhP resonances have mainly focused on nanoresonators with cylindrical symmetry, where the excitation source is mainly oriented perpendicular to the symmetry axis. With such geometries, light is able to efficiently couple to dipole and monopole resonances.^{21,40,41} However, thus far, the excitation of higher-order localized SPhP resonances with more exotic near-field radiation patterns, such as those theoretically predicted and observed for cubic plasmonic nanoparticles,^{37–39} have remained absent in the literature.

In this article, we experimentally and theoretically explore the far- and near-field behavior and aspect-ratio (shape) driven evolution of high-order localized SPhP resonances that occur in arrays of three-dimensional rectangular pillars. These structures are etched into semi-insulating, 4H-silicon-carbide substrates, similar to efforts previously reported from our group.^{21,41} A combination of the high structural asymmetry of these optical resonators, low optical losses, as well as the relative size of each pillar axis, leads to the excitation and spectroscopic observation of many high-order resonances with complex, three-dimensional, near-field radiation patterns. Through polarized reflectance measurements and finite-element-method simulations we are able to explore the polarization selection rules of the localized SPhP resonances and their evolution with increasing aspect ratio ($AR = \text{length}/\text{width}$). Interestingly, for many of the resonances we find that not only does the excitation energy vary with changing AR , but that the modal order also evolves as this quantity is increased, thus resulting in a splitting of the AR -driven dispersion of specific resonances. This is in contrast to conventional resonances that exhibit only an evolving excitation energy, while preserving the modal order. Furthermore, despite the degree of control over both the resonance energies and near-field profiles that varying AR can provide in such three-dimensional rectangular structures, such an investigation has remained elusive in literature, even for metal-based SPP systems. This is largely due to the difficulty in producing three-dimensional, rectangular plasmonic nanoparticles with well-controlled dimensions, a high degree of monodispersity, and low optical losses, where the latter two properties significantly broaden any resonances, resulting in strongly overlapping modes that are difficult to separate and/or distinguish. In this work, such challenges are overcome by the low optical losses of SPhPs in silicon carbide and the use of top-down fabrication techniques that produce highly uniform pillar arrays,²¹ providing exceptionally narrow localized SPhP resonances. The understanding we present here is critical to both sensing and enhanced emitter applications, where knowledge of the polarization selection rules enables one to tailor resonances in order to achieve more efficient near-field coupling between the nanostructure and the local emitter, molecule or other polariton source or for the more efficient design of polariton-based thermal emitters, with the modal behavior dictated by the near-field radiation patterns.^{42,43}

To study the excitation of multipolar localized SPhP resonances, we perform polarized reflectance measurements on fixed-height ($H = 950$ nm), fixed-width ($W = 400$ nm), rectangular-shaped, semi-insulating 4H-SiC pillars that vary in length ($L = 400 - 6400$ nm) and therefore aspect ratio ($AR = L/W = 1 - 16$). These pillars are patterned on a square grid with a pitch (P) that is 500 nm larger than the pillar length (i.e., $P = L + 500$ nm) to ensure that near-field coupling effects are not significantly contributing to the resonance behavior.⁴¹ Figures 1a and b show oblique and top-view scanning electron microscope (SEM) images of a representative SiC pillar array that depicts the general geometry for the samples studied. To excite localized SPhP resonances, polarized reflectance measurements are performed with the incident polarization oriented either parallel or perpendicular to the long axis of the pillars, as indicated in Figure 1. By selecting a single polarization orientation for each

measurement, we are able to effectively isolate localized SPhP resonances that are excited along the length and width of the pillar, since, in general, the incoming light couples to resonant modes that have a net dipole moment component that is oriented parallel to the incoming polarization.

Results/discussion

The influence of the pillars upon the resonant spectra is clearly observed in Figure 2a and b, which show the results of polarized FTIR reflectance measurements performed on un-patterned 4H-SiC (black curve) and the $AR=4$ pillar array (red curve), with a 22° weighted average angle of incidence and polarization oriented parallel (R_{\parallel}) and perpendicular (R_{\perp}) to the length of the pillars, respectively. As demonstrated in the black spectrum in Fig. 2a and b, between $\omega_{TO} = 797\text{cm}^{-1}$ and $\omega_{LO} = 973\text{cm}^{-1}$ the bulk SiC exhibits nearly 100% reflectance. This is due to the effective screening of radiation by oscillating lattice charges driven by the polar optical phonons. Comparison of the pillar reflectance spectra with that obtained for the bare substrate reveals clear deviations resulting from the excitation of localized SPhP resonances. As indicated by the arrows in Figure 2a, the parallel polarization reveals five modes that are observed in the range of $864-953\text{cm}^{-1}$. Similarly, for the perpendicular polarization, (Figure 2b), six resonances appear in the reflectance spectrum, over the spectral range of $885-961\text{cm}^{-1}$. For both polarizations, the sharp peaks that occur at 837cm^{-1} (labeled as P_1 and marked by a vertical dashed line in Figures 2a and 2b) and 964cm^{-1} (labeled as P_0) are associated with zone-folded LO phonons of 4H-SiC with a reduced wave vector of $x=1$ and $x=0$, respectively.⁴⁴ Interestingly, the P_1 mode is not infrared active, as confirmed by its absence from reflectance measurements of the bare SiC substrate. However, the P_1 phonon peak is observed with increasing amplitude as the localized SPhP resonances spectrally approach the P_1 phonon frequency. The existence of coupling effects between the P_1 phonon and localized SPhP resonances is further corroborated by the AR dependence of reflectance measurements that are shown in Figure S1 of the Supporting Information, where the P_1 mode clearly strengthens as the localized SPhP resonances spectrally approach and cross through this phonon mode, resulting in a Fano-like interference during the crossing. This observation is consistent with our previous findings within cylindrical nanopillars.²¹ Although interesting, a detailed discussion of this phenomena is beyond the scope of this paper, therefore we defer further studies of this interaction to a later date.

As demonstrated in Figure 2 a and b, for elongated pillars with structural asymmetry (i.e., $L \neq W \neq H$), each polarization orientation excites distinct localized SPhP resonances, similar to plasmonic nanostructures with structural asymmetries such as triaxial ellipsoids.^{24,45-47} For the $AR=4$ reflectance measurements, only a single localized SPhP resonance (labeled as L_{000} in Figure 2a and b) deviates from this behavior and is observed for both orthogonal polarizations at the same energy. Previously, it was demonstrated that this mode has a longitudinal nature and was referred to as a 'monopolar' resonance due to the abnormal near-field distribution that results from the attachment of the pillars to the negative permittivity SiC substrate.^{21,41}

To model the far- and near-field resonant behavior of the rectangular pillars, we perform full-wave electromagnetic simulations of the polarized pillar reflectance using the finite element method (FEM) calculations in COMSOL Multiphysics. The pillar geometry is modeled using the nominal values for the pillar array L, W, H and P , taking care to account for the rounding of the corners and edges of the

pillars, to ensure that the geometry matched the fabricated pillar structures as closely as possible (see METHODS). Simulations of R_{\parallel} and R_{\perp} for the $AR=4$ pillar array (green curve in Fig. 2a and b, respectively) semi-quantitatively agree with the corresponding reflectance measurement. Overall, despite differences in the linewidths, presumably due to imperfect fabrication, the simulated spectral positions of the resonances are in excellent agreement with measurements. In addition, we also simulate the polarized reflectance spectra (density plot) for the $AR=1-12$, as shown in figure 2c and d for parallel and perpendicular polarization, respectively. These plots present the differential reflectance ($\Delta R_p = R_{\text{SiC}}^p - R_{\text{SiC \& pillars}}^p$, where p denotes the polarization orientation, as introduced earlier). For both polarizations, trends in the simulated resonance shifts displayed in the density plots (white shaded, low-reflectance regions) are in excellent agreement with the experimentally measured resonance positions (symbols) for all AR studied. While experimental measurements were performed on arrays with $AR=1-16$, simulations were only possible up to $AR=12$, so we only present this dataset. Two additional resonances do appear in the simulations of the parallel polarization that are absent from reflectance measurements (found at spectral positions $\omega=926$ and 935 cm^{-1}). However, due to the significantly weaker amplitudes of these resonances in comparison to the other measured modes, it is possible that these resonant features are below the detection limit of our system or are difficult to detect due to additional broadening.

In addition to simulations of the pillar reflectance spectra, we are also able to extract the near-field charge distributions for each localized SPhP resonance. Figure 3 shows the simulated transverse near-field charge distributions for the $AR=4$ pillar array at normal incidence. Although we have also calculated the charge distributions for an angle of incidence of $\theta=22^\circ$ to match our experimental conditions, we find that the near field charge profiles are difficult to interpret due to charge inhomogeneities that are induced by non-uniform illumination of the pillars from a unidirectional light source; therefore, we limit our discussion to the case of normal incidence. We do note that as shown in Figure S2 of the supporting information, simulations reveal negligible changes in the spectral positions of localized SPhP resonances when excited by normal or off-normal incident light, indicating that the fundamental behavior of the resonances is independent of incident direction. As shown in Figure 3, the resonant charge density profiles of the $AR=4$ pillars take on two distinct forms; either the charge is primarily distributed along the 1) pillar edges and corners or 2) pillar faces. Based on this, hereafter we will refer to these distributions as edge and face modes, respectively. These findings are consistent with both calculations³⁹ and measurements³⁸ of the modal charge distributions for the strongest resonances of cube-shaped nanoresonators. However, we find that the rectangular nanopillars studied in this work are capable of supporting many higher order modes that can be thought of as multipolar extensions of the modes found in nanocubes. In Figure 2 and 3 we label resonances as M_{lwh}^p , where $M=E$ or F to denote the resonance as an edge or face mode, respectively; $p=\perp$ or \parallel identifies the excitation polarization and l, w and h are integers that indicate the number of charge nodes (i.e., points where charge polarity changes sign) that exist along the pillar edges or faces along the length, width, and height of the pillars, respectively. For edge modes, the indices l and w are determined by the number of nodes along the top edges of the pillar where the charge density profile is least affected by substrate effects and the most defining characteristics of the modes occur.

For the parallel polarized case, the lowest energy resonance E_{100}^{\parallel} is identified as a transverse dipole mode (see Figure 3a), as indicated by the existence of only a single node along the pillar length. This

mode has been well studied in cylindrical SiC pillar arrays.^{21,41} In contrast, at $AR = 4$, the lowest energy transverse resonances E_{211}^{\perp} that is excited by the perpendicular polarization is not a simple dipole mode, as shown in Figure 3e. Rather, this mode exhibits a modal profile with charge separation along all three pillar axes, including the length that is orthogonal to the incident polarization, demonstrating the fact that rectangular pillars are able to support non-homogeneous polarization configurations, not accessible in pillar geometries with higher symmetry (e.g., cylinders). As shown in Figures 3b-i, higher energy transverse resonances correspond to higher-order localized SPhP excitations that exhibit many charge density nodes along the three pillar axes. In general, the excited modes are either characterized by high charge concentrations at the pillar corners and edges (edge modes, E_{lwh}^p) or charge distributed across the pillar faces (face modes, F_{lwh}^p). Similar to the results of previous calculations for ionic crystal cubes³⁹ and experiments on metallic nanocubes,^{37,38} we find that the majority of resonances are edge modes that are excited at photon energies lower than those needed to excite face modes. For both types, the presence of the substrate strongly modifies the charge distribution near the base of the pillar, which breaks the top-bottom charge distribution symmetry that is typical of isolated cube shaped plasmonic nanoparticles.^{37,39} This is especially apparent for E_{301}^{\parallel} and E_{522}^{\parallel} , which exhibit many charge density nodes along the top of the pillar, but only show a single node along the pillar base. This top-bottom asymmetry of the charge distribution leads to a small longitudinal polarization component for the resonances. However, by calculating the dipole moments of the resonant charge distributions along the pillar axes, we find that this longitudinal component of the mode is over an order of magnitude weaker than the dominant transverse counterpart.

As briefly introduced in Figures 2c and d, simulations and measurements show that resonances can be tuned over a broad spectral range by elongating only a single axis of the rectangular pillars ($AR = 1-12$). Resonances can be further tuned by manipulating the dimensions of all three of the pillar axes, as done for triaxial ellipsoids;⁴⁵ however, to simplify our discussion we concentrate on varying only a single pillar axis. At $AR = 1$, both R_{\square} and R_{\perp} yield equivalent resonances due to the square symmetry of the pillar cross-sections. As AR is increased and cross-sectional symmetry is broken (i.e., $L \neq W$), the M_{lwh}^{\parallel} and M_{lwh}^{\perp} resonances spectrally separate, as observed by comparing the AR evolution of R_{\parallel} and R_{\perp} modes shown in Figures 2c and d (symbols), respectively. Thus, as previously discussed for the case of $AR = 4$ and further corroborated here, the rectangular cross-section results in the excitation of distinct resonances associated with each pillar axis. In general, the transverse resonances excited by light polarized parallel (perpendicular) to the pillar width redshift (blueshift) with increasing AR . Furthermore, we find that as AR increases, the SiC pillars are capable of supporting additional higher order transverse modes that are not supported at smaller AR s (e.g., this is clear for the modes represented by \blacklozenge symbols in Figure 2c).

In addition to the broad array of Edge and Face-oriented transverse modes, the so-called ‘monopole’ resonance, L_{000} remains spectrally degenerate for both polarizations over the entire range of AR s. However, in addition to the L_{000} mode, we also find higher-order longitudinal resonances L_{101}^{\square} and L_{200}^{\perp} (+ symbols shown in Figures 2c and d) that are spectrally degenerate. These resonances occur at higher frequency than L_{000} and are only optically active at larger aspect ratios ($AR \geq 4$). Similar to L_{000} , the longitudinal nature of L_{101}^{\square} and L_{200}^{\perp} is confirmed by the spectral degeneracy of the resonances

excited by both orthogonal polarizations and by angle of incidence measurements, revealing that a surface-normal polarization component is necessary in order to excite these modes. This is demonstrated in figure 4a, which shows the measured reflectance spectra of the $AR=7$ nanostructure measured at $\theta \approx 0^\circ$ and 22° (see Methods section) with light polarized perpendicular to the pillar length. At off-normal angles $\theta \approx 22^\circ$ both L_{000} and L_{200}^\perp resonances are clearly observed (red curve); however, near normal incidence $\theta \approx 0$ (black curve) these modes are extinguished due to the absence of a longitudinal polarization component. This behavior is in excellent agreement with simulations, as shown in Figure 4b. Although Figures 4a and b only show the results of measurements and simulations performed with the perpendicular polarization, the parallel polarization measurements and simulations of L_{000} and L_{101}^\parallel also exhibit this behavior. However, the demonstration of such behavior is much clearer for R_\perp , since L_{000} and L_{200} are more clearly spectrally separated from neighboring resonances. Figure 4c shows the simulated charge density profile for L_{000} that occurs near $\omega = 884 \text{ cm}^{-1}$ at $AR=7$. A significant portion of charge is concentrated near the base of the pillar, which is compensated by charge of the opposite polarity that is distributed across the substrate surface between the pillars. This is consistent with a monopole mode that has been discussed in previous work.^{48,21,40,41} The monopole nature of L_{000} is further corroborated by a strong concentration of the electric field underneath the pillar base, as indicated by the field plot shown in Figure 4d. As predicted in prior work,^{21,41} and as evidenced by our angle-dependent reflectance measurements, such a mode is not directly excited, rather it results from a longitudinal excitation that interacts with the substrate, yielding a monopolar charge distribution and near-field profile for both incident polarizations. Interestingly, simulations reveal distinct charge density profiles for the two degenerate resonances L_{200}^\perp and L_{101}^\parallel , shown in Figures 4e and f, respectively, despite the fact that these modes are spectrally degenerate. Furthermore, these resonances also differ by the fact that L_{200}^\perp couples to radiation at all $AR > 4$, while L_{101}^\parallel is only observed at $AR > 7$ (see Figure 2). These modal differences for the two polarizations are especially interesting given that the resonant energies of the two modes are nearly identical, with a separation of only $\Delta\omega = 0.06 \text{ cm}^{-1}$ according to simulations. This spectral separation is even smaller than the simulated spectral separation between the monopole mode excited by each polarization, $\Delta\omega = 0.35 \text{ cm}^{-1}$, where the modal profiles are nearly identical for both orthogonal polarizations. In general, the L_{000} , L_{101}^\parallel and L_{202}^\parallel charge density distributions, shown in Figures 4 c,e, and f, respectively, are preserved throughout the AR range where the modes are observed, making their near-field characteristics highly predictable.

The combined data from reflectance measurements and simulations reveal three distinct forms of localized SPhP modes that have different AR and polarization dependencies: 1) longitudinal (discussed above) and transverse resonances that 2) retain their near-field charge distributions with changing AR and 3) those that evolve with AR . For the second type, the retention of the near-field distribution results in a ‘stretching’ of the modal profile without changing the overall number nodes as the pillars are elongated (i.e., M_{lwh}^p remains constant for all AR s). Due to this behavior we refer to these resonances as transverse ‘static’ modes. The observed modes that fall into this category include: E_{100}^\parallel , F_{212}^\parallel (resonances designated by ■ and ● symbols in Figure 2c) as well as all of the transverse perpendicular modes E_{211}^\perp , E_{233}^\perp , E_{212}^\perp , F_{111}^\perp , F_{011}^\perp (resonances designated by symbols: □, ▽, ◇ and ○, respectively, in Figure 2d). Similar to the longitudinally excited resonances, these modes are important due to the fact

that their near-field modal profiles are highly predictable and remain unchanged regardless of the pillar AR . Furthermore, this behavior allows the near-field characteristics of these modes to be exploited over a wide range of energies, which is important for sensing applications that have specific frequency requirements and distinct spectral polarization selection rules.

Similar to the transverse static modes, the third type of resonance is also transverse in nature. However, simulations indicate that the resonant charge density profiles of this third class are not static over the entire range of ARs investigated. Rather, as AR is increased, the charge is redistributed across the surface of the pillar in a non-trivial way, where the number of charge nodes are not preserved as the pillars are elongated (i.e., M_{lwh}^p varies as AR changes). As such, we refer to these resonances as transverse ‘dynamic’. Such an effect is exemplified by the three resonances that appear in the simulations of $\Delta R_{||}$, shown in Figure 5a (black, red, and green curves serve as guides to the resonance centers). Similar to all other parallel polarized resonances discussed previously, the simulated reflectance spectra show that these modes continuously redshift with increasing AR . However, as shown in Figure 5b-d and indicated by the mode labels in Figure 5a, for these three modes, charge is redistributed across the pillars as AR is increased. This is especially interesting, since the reflectance spectra show no indication of an evolving modal profile. This behavior is especially apparent for the resonance that is activated at the smallest ARs (black curve in Figure 5a), where the charge density profiles for this mode exhibit three major charge distribution patterns (see Figure 5b): $E_{120}^{||}$, $E_{321}^{||}$ and $E_{301}^{||}$, with modal transitions occurring near $AR=1.8$ and 3.3 . Similar behavior is observed for the other two resonances shown in Figure 5c-d. This charge distribution evolution enables one to significantly alter the near field charge distribution of resonances while having only a minor effect on the resonance energy. This property can have a significant impact on the local enhancement of nanoscale emitters and interaction with molecular vibrational modes for surface enhanced infrared absorption (SEIRA), since such modes enable one to custom tailor the near-field distributions. In addition, these effects also enable polarization and modal control of narrow-band, solid-state thermal emitters using localized SPhPs.^{42,43}

Conclusions

Through a combination of experiment and simulations we have demonstrated the ability to locally control the near-field profiles and resonant energies of localized SPhP resonances in rectangular pillars by adjusting the length of only a single pillar axis. The rectangular shape of the pillars plays a critical role in this control, since the squared off edges and corners of the pillar allows for the optical excitation of over 17 distinct, polarization-sensitive, localized SPhP modes that cannot be excited in structures with higher degrees of symmetry (e.g., spheres, cylinders, etc...). These optically-active resonances are extremely diverse in nature, ranging from a simple dipole mode to complex, high-order multipole resonances that exhibit intricate, three-dimensional, near-field profiles that are able to concentrate charge and electric fields along the faces, edges and/or corners of the pillars. As demonstrated in this work, the resonant energies for many of the observed localized SPhP resonances can be tuned without affecting the near-field profile of the mode by carefully selecting the length of pillar. This understanding provides a basis for exploiting the near-field characteristics of a particular mode over a wide energy range, which is especially important for applications where matching of the resonance energy and near-field distribution are required over a broader spectral range. In contrast, we also find that a series of resonances undergo a renormalization of the charge and electric field

distribution with increasing AR , offering in this case flexibility in controlling the near-field characteristics of localized SPhP resonances, while retaining the resonance frequency. Overall, this understanding is imperative to achieving efficient coupling between the resulting modal symmetry of the pillars to that of a local emitter, molecule or other polariton source, where a matching of the near-field distribution can be critical. Furthermore, our demonstration that these resonances can be predicted using electromagnetic modeling, even for these highly complicated resonance spectra, clearly indicates that user-design of the resonance frequency, polarization properties and modal profile can be achieved.

Methods

Sample preparation

Silicon carbide pillars were formed on the surface of semi-insulating 4H-SiC substrates. To fabricate the pillars, electron-beam lithography and lift-off techniques were used to produce a Al/Cr hard mask pattern that defined the footprint of each pillar array. Subsequently, a reactive ion etch with equal partial pressures of SF_6 and Ar at a power of 150 W was performed for 38 minutes in order to etch away the substrate, defining the height of the pillars. A wet chemical etch was used to remove the hard metal mask. To remove residual fluorine from the surface a commercial PlasmaSolv[®] treatment was performed. Each of the resulting pillar arrays consist of rectangular pillars with a designed height of $H = 950$ nm, length of $L = 400$ nm, and a width of $W = AR \cdot L$, where the width is dependent upon the aspect ratio selected for each array. The nominal aspect ratios of the pillars fabricated and measured are $AR = 0.5, 0.75, 1, 1.25, 1.5, 1.75, 2, 2.5, 4, 5, 6, 7, 8, 10, 12, 16$. The pillars are designed on a square lattice with a pitch of $P = W + 500$ nm, which guarantees that the pillars are well separated in order to minimized interpillar interactions. In general, the length and width of the pillars is $16 \pm 4\%$ smaller than the nominal dimensions, while the pillar aspect ratios differ from the designed values by $\pm 5\%$, as informed by SEM.

Reflectance spectroscopy

Reflectance measurements are performed using a Bruker 80v spectrometer with microscope attachment (Hyperion 1000). The microscope is fitted with an all-reflective, reverse Cassegrain, microscope objective that illuminates the sample with a range of incident angles that varies over the range of $\theta = 15 - 30^\circ$. Near normal incidence reflectance measurements are performed with a mid-infrared, ZnSe focusing objective (Innovation Photonics) that illuminates the sample with a range of incident angles that varies from $\theta = 0 - 4.5^\circ$. A mid-infrared, linear wire-grid polarizer that is placed in the microscope beam path enables the incident radiation to be nominally polarized either parallel or perpendicular to the long edge of the pillars. Due to the finite size of the pillar arrays ($50 \times 50 \mu\text{m}$), a set of apertures are used to limit the microscope field of view, so only spectra from the pillar array is collected. The utilization of the slits reduces the angle of incidence from the ZnSe even further. Measurements are normalized to the reflectance of a gold mirror and the reflectance of the 4H-SiC substrate.

Modeling

Near- and far-field optical properties are calculated by determining the Full wave, 3D electrodynamic solutions to Maxwell's equations via the RF package of the finite element method simulation software COMSOL. For these simulations, the pillar geometry was represented as a triaxial cuboid with rounded corners and edges. The dimensions used for the rounding of the pillar edges and corners was informed by SEM images of the fabricated pillars. In addition to being more true to the actual structure of the fabricated pillars, the geometric rounding also reduces calculation artifacts and instabilities that occur for structures with sharp corners. Numerical simulations are performed on a single pillar while employing periodic boundary conditions in order to account for interactions between neighboring nanopillars. The reflectance spectra and surface charge density distributions were calculated over the spectral range of the SiC Reststrahlen band for aspect ratios in the range of $AR=1-12$ at increments of $\Delta AR=0.25$. Although, nanostructures were fabricated with aspect ratios up to $AR=16$, we only perform calculations up to $AR=12$ due to demanding nature of these computations. All simulations were performed with two different angles of incidence, $\theta=0^\circ$ and 22° , which approximate the average angle of incidence for the two microscope objectives used in the reflectance measurements. Furthermore, in order to excite both longitudinal and transverse resonances the incident radiation is p-polarized in order to guarantee a polarization component oriented along the height of the pillar for off-normal angles of incidence. To improve clarity of the surface charge distributions for the transverse modes in Figure 3, the simulations shown are calculated with normal incidence. Both normal and off-normal incident radiation simulations show surface charge concentrated in the same positions of the pillar. However, unlike the normal incidence case, off-normal radiation produces a gradient in the magnitude of the charge density across the pillar. This charge density gradient depends on the orientation of the incoming wave vector used in the simulation. Since longitudinal modes are only excited by off-normal radiation, the surface charge density profiles shown for these modes (Figure 4) are calculated with a 22° angle of incidence.

Acknowledgments

The authors would like to thank Yiguo Chen and Stefan Maier of Imperial College London for infrared grazing angle measurements not presented in this work. Electron beam lithography was performed at NIST Center for Nanoscale Science and Technology. Funding for the NRL authors was provided by the Office of Naval Research & administered by the Naval Research Laboratory Nanoscience Institute. C.T.E., A.J.G, and F.J.B acknowledge support from the National Research Council and the American Society for Engineering Education postdoctoral fellowship programs.

Figure Captions

Figure 1: Scanning electron micrograph of optical resonator array. (a) off-axis and (b) top view scanning electron micrograph of the $AR=6$ optical resonator array. As indicated in both panels, the major component of the incoming light polarization is oriented either parallel or perpendicular to the elongated edge of the pillars. Panel (b) displays the important dimensions of the pillar array geometry.

Figure 2: General results of reflectance measurements and simulations. (a-b) Results of reflectance measurements performed on unpatterned SiC (black curve) and the $AR=4$ pillar array (red curve), as

well as the simulated reflectance (green curve). All measurements and simulations are performed with average 22° off-normal angle of incidence and incoming polarization oriented (a) parallel (R_{\parallel}) and (b) perpendicular (R_{\perp}) to the elongated edge of the pillars (L). SPhP bands are indicated by arrows and zone folded LO bands are labeled P_0 and P_1 . (c-d) Measurements and simulations of the aspect ratio evolution of localized SPhP resonance energies for the (c) parallel and (d) perpendicular polarizations. The middle panel for (c) and (d) demonstrates how the measured spectral position of the localized SPhP resonances evolve with pillar aspect ratio (symbols), for their respective incident polarizations. The measured spectral positions of localized SPhP resonances (symbols) are overlaid for comparison on the finite element method simulations of the differential reflectance $\Delta R = R_{SiC} - R_{SiC \& Pillars}$, which is represented by the density plot, with white and black shaded areas corresponding to low and high reflectance, respectively. The left and right panels (c) and (d) show the substrate normalized reflectance measurements of the $AR=1$ and $AR=12$ pillar arrays, respectively.

Figure 3: Near-field behavior of localized surface phonon polariton resonances for $AR=4$ pillars. Surface charge densities for transverse localized SPhP resonances excited by light polarized (a-d) parallel and (e-i) perpendicular to the pillar length and normally incident radiation (see Methods section for calculation details). Red and blue shading represent charge densities with opposite polarity. Panels (a-d) and (e-i) are plotted using separate color scales (see panels a and e insets). The parameters h, k and l that enumerate the number of charge nodes are determined by the edges and faces indicated by their respective guidelines in panels (a,d,e and h). In addition, the symbols shown for each panel corresponds to the symbols used for each similarly marked resonance shown in the spectra of Figure 2.

Figure 4: Comparison resonances excited by normal and off-normal incident radiation. (a) Measured and (b) simulated reflectance spectra for the $AR=7$ pillar array with off-normal (red curve) and near-normal (black curve) incident light. Symbols with arrows and vertical guidelines indicate the two longitudinal localized SPhP resonances that are quenched by extinguishing the polarization component oriented along the height of the pillar at normal incidence. (c) shows the surface charge density profile and (d) shows the electric field under the base of the pillar for the L_{000} monopole mode. (e) and (f) show the surface charge density profile for the parallel and perpendicular polarized modes for L_{200}^{\perp} and L_{101}^{\parallel} , respectively. All modal profiles are shown for $AR=7$ pillars. Symbols in the lower left corner of (c)-(f) are using to identify these resonances in Figure 2.

Figure 5: Evolution of surface charge distribution with AR for transverse dynamic resonances. (a) Simulated reflectance of SiC Rectangular pillars with increasing AR , where white and black shaded areas correspond to low and high reflectance, respectively. The three curves indicate the three transverse dynamic resonances. (b-d) Shows the calculated redistribution of surface charge for the three transverse dynamic resonances as the pillar AR is increased. Arrows mark major changes that occur in the charge distribution.

1. Maier, S. A. *Plasmonics : fundamentals and applications*. (Springer, 2007).

2. Giannini, V., Fernández-Domínguez, A. I., Heck, S. C. & Maier, S. A. Plasmonic Nanoantennas: Fundamentals and Their Use in Controlling the Radiative Properties of Nanoemitters. *Chem. Rev.* **111**, 3888–3912 (2011).
3. Li, M., Pernice, W. H. P. & Tang, H. X. Tunable bipolar optical interactions between guided lightwaves. *Nat. Photonics* **3**, 464–468 (2009).
4. Pyayt, A. L., Wiley, B., Xia, Y., Chen, A. & Dalton, L. Integration of photonic and silver nanowire plasmonic waveguides. *Nat. Nanotechnol.* **3**, 660–665 (2008).
5. Oulton, R. F., Sorger, V. J., Genov, D. A., Pile, D. F. P. & Zhang, X. A hybrid plasmonic waveguide for subwavelength confinement and long-range propagation. *Nat. Photonics* **2**, 496–500 (2008).
6. Lezec, H. J. *et al.* Beaming light from a subwavelength aperture. *Science* **297**, 820–822 (2002).
7. Nagpal, P., Lindquist, N. C., Oh, S.-H. & Norris, D. J. Ultrasoother patterned metals for plasmonics and metamaterials. *Science* **325**, 594–597 (2009).
8. Kawata, S., Inoué, Y. & Verma, P. Plasmonics for near-field nano-imaging and superlensing. *Nat. Photonics* **3**, 388–394 (2009).
9. Schnell, M. *et al.* Controlling the near-field oscillations of loaded plasmonic nanoantennas. *Nat. Photonics* **3**, 287–291 (2009).
10. Ferry, V. E., Sweatlock, L. A., Pacifici, D. & Atwater, H. A. Plasmonic Nanostructure Design for Efficient Light Coupling into Solar Cells. *Nano Lett.* **8**, 4391–4397 (2008).
11. Nolde, J. A. *et al.* Resonant quantum efficiency enhancement of midwave infrared nBn photodetectors using one-dimensional plasmonic gratings. *Appl. Phys. Lett.* **106**, 261109 (2015).
12. Raschke, G. *et al.* Gold Nanoshells Improve Single Nanoparticle Molecular Sensors. *Nano Lett.* **4**, 1853–1857 (2004).
13. Anker, J. N. *et al.* Biosensing with plasmonic nanosensors. *Nat. Mater.* **7**, 442–453 (2008).

14. Kabashin, A. V. *et al.* Plasmonic nanorod metamaterials for biosensing. *Nat. Mater.* **8**, 867–871 (2009).
15. Li, M. *et al.* Harnessing optical forces in integrated photonic circuits. *Nature* **456**, 480–484 (2008).
16. Engheta, N. Circuits with light at nanoscales: optical nanocircuits inspired by metamaterials. *Science* **317**, 1698–1702 (2007).
17. Caglayan, H., Hong, S.-H., Edwards, B., Kagan, C. R. & Engheta, N. Near-Infrared Metatronic Nanocircuits by Design. *Phys. Rev. Lett.* **111**, 073904–1–073904–5 (2013).
18. Nagao, T. *et al.* Plasmons in nanoscale and atomic-scale systems. *Sci. Technol. Adv. Mater.* **11**, 054506 (2010).
19. Law, S., Podolskiy, V. & Wasserman, D. Towards nano-scale photonics with micro-scale photons: the opportunities and challenges of mid-infrared plasmonics. *Nanophotonics* **2**, (2013).
20. Caldwell, J. D. *et al.* Low-loss, infrared and terahertz nanophotonics using surface phonon polaritons. *Nanophotonics* **4**, 44–68 (2015).
21. Caldwell, J. D. *et al.* Low-Loss, Extreme Subdiffraction Photon Confinement via Silicon Carbide Localized Surface Phonon Polariton Resonators. *Nano Lett.* **13**, 3690–3697 (2013).
22. Boltasseva, A. & Atwater, H. A. Low-Loss Plasmonic Metamaterials. *Science* **331**, 290–291 (2011).
23. West, P. R. *et al.* Searching for better plasmonic materials. *Laser Photonics Rev.* **4**, 795–808 (2010).
24. Bohren, C. F. & Huffman, D. R. Absorption and scattering of light by small particles. (2004). Available at: <http://public.eblib.com/choice/publicfullrecord.aspx?p=481657>.
25. Hillenbrand, R., Taubner, T. & Keilmann, F. Phonon-enhanced light–matter interaction at the nanometre scale. *Nature* **418**, 159–162 (2002).
26. Caldwell, J. D. *et al.* Sub-diffractive volume-confined polaritons in the natural hyperbolic material hexagonal boron nitride. *Nat. Commun.* **5**, 5221 (2014).

27. Dai, S. *et al.* Subdiffractive focusing and guiding of polaritonic rays in a natural hyperbolic material. *Nat. Commun.* **6**, 6963 (2015).
28. Li, P. *et al.* Hyperbolic phonon-polaritons in boron nitride for near-field optical imaging and focusing. *Nat. Commun.* **6**, 7507 (2015).
29. Krenn, J. R. *et al.* Design of multipolar plasmon excitations in silver nanoparticles. *Appl. Phys. Lett.* **77**, 3379 (2000).
30. Payne, E. K., Shuford, K. L., Park, S., Schatz, G. C. & Mirkin, C. A. Multipole plasmon resonances in gold nanorods. *J. Phys. Chem. B* **110**, 2150–2154 (2006).
31. Ghenuche, P., Cherukulappurath, S., Taminiau, T. H., van Hulst, N. F. & Quidant, R. Spectroscopic Mode Mapping of Resonant Plasmon Nanoantennas. *Phys. Rev. Lett.* **101**, 116805 (2008).
32. Sheikholeslami, S., Jun, Y., Jain, P. K. & Alivisatos, A. P. Coupling of Optical Resonances in a Compositionally Asymmetric Plasmonic Nanoparticle Dimer. *Nano Lett.* **10**, 2655–2660 (2010).
33. Sherry, L. J. *et al.* Localized Surface Plasmon Resonance Spectroscopy of Single Silver Nanocubes. *Nano Lett.* **5**, 2034–2038 (2005).
34. Zhang, S., Bao, K., Halas, N. J., Xu, H. & Nordlander, P. Substrate-Induced Fano Resonances of a Plasmonic Nanocube: A Route to Increased-Sensitivity Localized Surface Plasmon Resonance Sensors Revealed. *Nano Lett.* **11**, 1657–1663 (2011).
35. Wiley, B. J. *et al.* Maneuvering the Surface Plasmon Resonance of Silver Nanostructures through Shape-Controlled Synthesis. *J. Phys. Chem. B* **110**, 15666–15675 (2006).
36. Noguez, C. Surface Plasmons on Metal Nanoparticles: The Influence of Shape and Physical Environment. *J. Phys. Chem. C* **111**, 3806–3819 (2007).
37. Cortie, M. B., Liu, F., Arnold, M. D. & Niidome, Y. Multimode Resonances in Silver Nanocuboids. *Langmuir* **28**, 9103–9112 (2012).

38. Nicoletti, O. *et al.* Three-dimensional imaging of localized surface plasmon resonances of metal nanoparticles. *Nature* **502**, 80–84 (2013).
39. Fuchs, R. Theory of the optical properties of ionic crystal cubes. *Phys. Rev. B* **11**, 1732 (1975).
40. Wang, T., Li, P., Hauer, B., Chigrin, D. N. & Taubner, T. Optical Properties of Single Infrared Resonant Circular Microcavities for Surface Phonon Polaritons. *Nano Lett.* **13**, 5051–5055 (2013).
41. Chen, Y. *et al.* Spectral Tuning of Localized Surface Phonon Polariton Resonators for Low-Loss Mid-IR Applications. *ACS Photonics* **1**, 718–724 (2014).
42. Greffet, J.-J. *et al.* Coherent emission of light by thermal sources. *Nature* **416**, 61–64 (2002).
43. Schuller, J. A., Taubner, T. & Brongersma, M. L. Optical antenna thermal emitters. *Nat. Photonics* **3**, 658–661 (2009).
44. Nakashima, S. & Harima, H. Raman Investigation of SiC Polytypes. *Phys. Status Solidi A* **162**, 39–64 (1997).
45. Guzatov, D. V., Klimov, V. V. & Pikhota, M. Y. Plasmon oscillations in ellipsoid nanoparticles: Beyond dipole approximation. *Laser Phys.* **20**, 85–99 (2010).
46. Kalkbrenner, T., Håkanson, U. & Sandoghdar, V. Tomographic Plasmon Spectroscopy of a Single Gold Nanoparticle. *Nano Lett.* **4**, 2309–2314 (2004).
47. Aizpurua, J. & Hillenbrand, R. in *Plasmonics: from basics to advanced topics* **167**, 151–176 (Springer, 2012).
48. Çetin, A. E. *et al.* Monopole antenna arrays for optical trapping, spectroscopy, and sensing. *Appl. Phys. Lett.* **98**, 111110 (2011).