

U. S. DEPARTMENT OF COMMERCE
 WASHINGTON, D. C. 20234
 NATIONAL BUREAU OF STANDARDS
 PROVISIONAL CERTIFICATE OF ANALYSES
 GILDING METAL STANDARDS
 FOR

OPTICAL EMISSION AND X-RAY SPECTROSCOPIC ANALYSIS

NBS No.	<u>1/</u> 1112 C1112	1113 C1113	1114 C1114
Element	<u>2/</u> Percent		
Cu	93.3 ₈	95.0 ₃	96.4 ₅
Zn	6.3 ₀	4.8 ₀	3.4 ₇
Sn	0.12	0.06 ₄	0.02 ₇
Ni	.10 ₀	.057	.021
Fe	.07 ₀	.04 ₃	.01 ₇
Pb	.057	.026	.012
P	.009	.008	.009

1/ Size and metallurgical condition: 1100 series are wrought samples 1 1/4 in. in diameter, 3/4 in. thick. C1100 series are chill-cast samples 1 1/4 in. square, 3/4 in. thick.

2/ Al, Mn, Ag, and Si also are present in small quantities in the standards, but these elements have not been certified.

The material for each standard was melted and cast at the Naval Research Laboratory, Washington, D. C. High-purity metals were used either directly or in the preparation of master alloys. Approximately 650-pound heats were melted under a charcoal cover in a high-frequency induction furnace and the molten metal cast on a massive water-cooled plate to provide rapid unidirectional solidification. The casting for each standard was about 27 in. in diameter and 3 1/2 in. thick.

The material for the chill-cast samples was obtained from the area of the casting nearest the chill-cast face. Samples were finished to a size 1 1/4 in. square, 3/4 in. thick, and each has the NBS number marked on the face opposite to the chill-cast or test surface. (In addition, a specimen serial number has been placed on one side face.)

(OVER)

The material for the wrought samples was obtained after removal of the chill-cast material and discard of about 3/4 in. thickness from the slab top. Strips of this material were forged, fully annealed, and finished to samples 1 1/4 in. in diameter, 3/4 in. thick.

The homogeneity of the standards material was investigated by metallographic studies and by optical emission and chemical analyses at the National Bureau of Standards; and by optical emission and chemical analyses by Task Group 3, Subcommittee V of ASTM Committee E-2*. The homogeneity was found to be satisfactory.


Samples for chemical analysis were prepared in the form of millings taken from the cross section of the finished samples of both the chill-cast and wrought material. Chemical analyses were made by R. K. Bell and E. E. Maczkowske, Standard Reference Materials Section, National Bureau of Standards, Washington, D. C.; A. E. LaRochelle, Elsie M. Penner, C. H. McMaster, and W. R. Inman, Department of Mines and Technical Surveys, Mines Branch, Ottawa, Ontario, Canada; Frederick V. Schatz and R. E. Hahn, Metal Physics Department, Revere Copper and Brass, Incorporated, Rome, N. Y.; Silve Kallmann, Ledoux and Co., Teaneck, New Jersey.

Caution should be observed in the use of the chill-cast samples in that determinations made on other than the chill-cast or test surface are not recommended because of the unidirectional solidification. Moreover, the chill-cast standards are designed for calibration in the analysis of samples prepared in the same manner. Samples prepared by other casting techniques may result in considerable bias.

Additional copper-base standards are in preparation and announcements of availability for these and other standards will appear in the technical literature.

* Task Group 3 cooperators:

Bridgeport Brass Co., Bridgeport, Conn., A. W. Young
Chase Brass and Copper Co., Waterbury, Conn., H. J. Smith
Mueller Brass Co., Port Huron, Mich., S. C. Richards
Olin Mathieson Chemical Corp., New Haven, Conn., R. G. Russell
Revere Copper and Brass, Inc., Rome, N. Y., F. V. Schatz (Chairman)
The Anaconda American Brass Co., Waterbury, Conn., J. P. Irwin
Titan Metal Mfg. Co., Bellefonte, Pa., W. M. Rumberger


W. Wayne Meinke, Chief
Analytical Chemistry Division

Washington, D. C. 20234
February 14, 1964