

Certificate

NBS-ICTA Standard Reference Material 760

DTA Temperature Standards (570 – 940 °C)

These standards include: natural quartz; analyzed reagent potassium sulfate, potassium chromate, barium carbonate, and strontium carbonate. They are for use in calibrating the temperature scale on differential thermal analysis and related thermoanalytical equipment under operating conditions. They are to be used only in the heating mode.

Transition Temperature Data (°C)

Material	Equilibrium Value [1]	DTA Mean Values	
		Extrapolated Onset	Peak
SiO ₂	573	571	574
K ₂ SO ₄	583	582	588
K ₂ CrO ₄	665	665	673
BaCO ₃	810	808	819
SrCO ₃	925	928	938

The extrapolated onset temperature is defined (Point A, Figure 1) as that temperature found by extrapolating the base line, prior to the peak, and the leading side of the peak to their intersection. The peak temperature (Point B, Figure 1) is defined as the temperature corresponding to the point of maximum deflection of the differential temperature curve.

Based on the mean value from 34 cooperating laboratories, the standard deviation was 5.8 °C, which includes the bias among laboratories as well as measurement errors. In the heating mode, onset and peak temperatures have about equal precision. However, the mean extrapolated onset temperatures are closer to the equilibrium transition temperatures.

The materials for these standards were furnished by the Committee on Standardization of the ICTA.

The International Test Program leading to the data on which certification is based was coordinated by H. G. McAdie, Chairman, ICTA Committee on Standardization.

Coordination of efforts leading to certification by NBS was under the chairmanship of O. Menis.


The technical and support aspects involved in the preparation, certification, and issuance of these Standard Reference Materials were coordinated through the Office of Standard Reference Materials by T. W. Mears.

Washington, D. C. 20234
June 11, 1971

J. Paul Cali, Chief
Office of Standard Reference Materials

(over)

The transition temperatures given are the means of values obtained on 28 different types of commercial or custom-made instruments, and do not necessarily agree with the equilibrium values [1]. Generally, values from DTA are somewhat higher than the equilibrium values and vary in a complex manner for different instruments and heating rates. Details of the instruments used, the test conditions and complete data will be given in an NBS Special Publication in the 200 series (in publication).



[1] Nat. Bur. Stand. (U.S.), Circ. 500 (1952).

Cooperating Laboratories

Dr. David E. Baum, Monsanto Australia Limited, West Footscray, Victoria, Australia
Prof. Marcel Bourgon, Université de Montréal, Montréal, Quebec, Canada
Dr. H. G. McAdie, Ontario Research Foundation, Sheridan Park, Ontario, Canada
Dr. Klaus Heide, Friedrich-Schiller-Universität, Jena, Germany
Dr. J. Wiegmann, Berlin, Germany
Dr. G. R. Cizeron, Université de Paris, Paris, France
Dr. M. Harmelin, C.N.R.S., Paris, France
Mme. J. Jegoudez, Université de Paris, Paris, France
Dr. M. Foldvari, Hungarian Geological Institute, Budapest, Hungary
Mr. J. Paulik, Technical University of Budapest, Budapest, Hungary
Prof. H. Kambe, University of Tokyo, Tokyo, Japan
Prof. C. Kato, Waseda University, Tokyo, Japan
Prof. K. Oinuma, Tokyo University, Tokyo, Japan
Prof. R. Otsuka, Waseda University, Tokyo, Japan
Mr. J. E. Kruger, National Building Research Institute, Pretoria, South Africa
Dr. R. S. Forsyth, Aktiebolaget Atomenergi, Studsvik-Nyköping, Sweden
Dr. G. Krien, Institut für Chemisch-Techn. Untersuchungen, Leverkusen, Germany
Prof. H. R. Oswald, Universität Zurich, Zurich, Switzerland
Dr. T. Peters, Universität Berne, Berne, Switzerland
Dr. H. G. Wiedemann, Mettler Instrumente A. G., Greifensee, Switzerland
Prof. L. G. Berg, Gosuniversitet, Kazan, U.S.S.R.
Prof. E. K. Kochler, Academy of Sciences of the USSR, Novosibirsk, USSR
Dr. I. S. Rassonskaya, Institut Obshehei i Neorganicheskoi Khimii, Moscow, USSR
Dr. G. O. Piloyan, Academy of Sciences of the USSR, Moscow, USSR
Mr. E. L. Charsley, Stanton Redcroft Limited, London, England
Dr. R. C. Mackenzie, The Macaulay Institute for Soil Research, Aberdeen, Scotland

Prof. D. A. Smith and Mr. J. Youren, Queen Mary College, University of London, London, England

Dr. P. K. Gallagher, Bell Telephone Laboratories, Murray Hill, N.J., U.S.A.

Prof. P. D. Garn, University of Akron, Akron, Ohio, U.S.A.

Dr. O. Menis, D. S. Bright, and J. T. Sterling, National Bureau of Standards, Washington, D.C., U.S.A.

Mr. T. D. Oulton, Englehard Minerals & Chemicals Corp., Edison, N.J., U.S.A.

Dr. R. K. Ware, Owens-Illinois, Toledo, Ohio, U.S.A.

International Confederation for Thermal Analysis Committee on Standardization:

Chairman		(Canada)	H. G. McAdie
Vice-Chairman		(U.S.A.)	P. D. Garn
Secretary		(U.K.)	R. C. Mackenzie
National Delegates		(France)	C. Mazieres
		(German D.R.)	K. Heide
		(Hungary)	F. Paulik
		(Japan)	H. Kambe
		(Sweden)	R. S. Forsyth
		(Switzerland)	H. G. Wiedemann
		(U.S.S.R.)	I. S. Rassonskaya
		(U.K.)	D. A. Smith
		(U.S.A.)	R. W. Pfeil
	Representative Delegates	ASTM	(U.S.A.)
ISO			Vacant
NBS		(U.S.A.)	O. Menis
Soc. Anal. Chem.		(U.K.)	C. J. Keatch
Ex-Officio Delegates	SAMA	(U.S.A.)	Vacant
	ICTA	(U.S.S.R.)	L. G. Berg
		(U.S.A.)	C. B. Murphy
		(U.K.)	R. C. Mackenzie
(U.K.)		J. P. Redfern	